

ARSENIC AGC33002

WHEAT AGC33003

FALLOW AGC33004

GREY AGC33005

WENGE AGC33006

Technical Specifications

Type of Test	Standard Test MS ISO13006	MS ISO13006
		300X300mm
Dimensions & Surface Quality		
Length & Width	± 0.6%	± 0.6%
Thickness	± 5%	± 5%
Straightness of Sides	± 0.5%	± 0.5%
Rectangularity	± 0.6%	± 0.6%
Surface Flatness		
Centre Curvature	± 0.5%	± 0.5%
Edge Curvature	± 0.5%	± 0.5%
Warpage	± 0.5%	± 0.5%
Surface Quality	≥ 95% free from Visible defects	≥ 95% free from Visible defects
Physical Properties		
Water Absorption	Group BIIa 3% < E ≤ 6%	Group BIIa 3% < E ≤ 6%
Breaking Strength	≥ 600N	≥ 600N
Modulus of Rupture	Min. 22N/mm ²	Min. 22N/mm ²
Surface Abrasion (PEI)	Class 2 - 4	Class 2 - 4
Crazing Test	No crazing	No crazing
Chemical Properties		
Chemical Resistance	Min. GB	Min. GB
Stain Resistance	Min. Class 3	Min. Class 3

Packing List

Size	Pcs/ctn	ctn/plt	m ² /ctn	kg/ctn	kg/plt
AGC 300x300mm	17	72	1.53	23kg	1656kg

Feruni
CERAMICHE
designed for luxury

No. 12, Jalan 51A/213, Seksyen 51A, 46050 Petaling Jaya, Selangor, Malaysia.
T: + 603 7784 7277 F: + 603 7784 7272 E: enquiry@feruni.com W: www.feruni.com